

PLASTOFLEX 71 Green

Frost-protecting wax for fruit trees

Property and Unit	Requirement	Method
Colour	light whitish	
Viscosity at 100 °C, mm ² /s, min.	5	ASTM D 445
Congealing point (rotational), °C, min.	48	ASTM D 938
Drop melting point, °C	52-62	ASTM D 127
Flash point (CL), °C, min.	200	ASTM D 92

PRODUCER and EXPORTER

Production plant:
BOGDÁNY PETROL Ltd.
H-4511 Nyírbogdány
Gyártelep
HUNGARY
Phone: +36-42/232-377
Fax: +36-42/232-227

Export Sales Office:
BOGDANY PETROL Ltd.
H-1117 Budapest
Fehérvári út 84/A.
HUNGARY
Phone: +36-1/324-2101
Fax: +36-1/324-2102
Email: export@bogdanypetrol.hu



ISO 9001 – ISO 14001